

Please find results for permeability of 10mm Sempatap sample.

Permeability, etc. see attached for definitions

WET CUP TEST	Thickness	Permeance of sample	Permeability	SD	DRF
5 samples	mm	Kg/s.m ² .Pa	Kg/s.m.Pa		
Sempatap	10	3.88E-09	3.88E-07	0.05	4.97

Again thanks for the sample materials.

Kind Regards

Paul

Dr Paul Baker
Centre for Research on Indoor Climate & Health
School of Built & Natural Environment
Glasgow Caledonian University
Glasgow
G4 0BA
t: +44 (0) 141 331 8185
e: pba3@gcal.ac.uk

Glasgow Caledonian University is a registered Scottish charity, number SC021474